HARDSCAPE PRODUCTS

www.hardscapeproducts.co.uk
**Telephone:** 01204 565 500 **Email:** enq@hardscape.co.uk
Hardscape Products Ltd., Eagley House, Deakins Business Park, Egerton, Bolton, Lancashire, BL7 9RP



# Mara

## Fuerana

Mara Fuerana, from Portugal, is a silver-grey/white granite for applications such as cladding, copings, kerbs, paving and setts.



| SPECIFICATION | SKU: GRA-POR-MAR-007 | |
|---|---|---|
| **Material** | Granite | |
| **Finish** | Bush Hammered, Flamed, Honed, Polished, Sandblasted, Sawn | |
| **Density** | - | 2630 kg/m³ |
| **GWP (total) kgCO2e** | ISO 14025 / EN 15804 | 0.035 per kg |
| **Compressive Strength** | BS EN 1926:2006 | 173 MPa LEV |
| **Compressive Strength (Freeze/Thaw Resistance)** | BS EN 1926:2006 | 183 / 190 MPa Mean |
| **PPV (Before/After)** | BS EN 7932:2003 | NPD |
| **Flexural Freeze/Thaw** | BS EN 12371:2010 | 13.0 / 15.8 MPa Mean |
| **Flexural Strength** | BS EN 12372:2006 | 12.1 MPa LEV |
| **Light Reflectance Value** | BS EN 84369:2008 | Bush Hammered 41.0 : Flamed 38.6 LRV |
| **Open Porosity** | BS EN 1936:2006 | 1.1% |
| **Slip Resistance** | BS EN 13036-4, BS 7976 | Sawn 61 (wet), 66 (dry) SRV/USRV |
| **Water Absorption** | BS EN 13755:2008 | 0.35% |
| **Abrasion Resistance** | BS EN 14157:2004 | 16.5mm |



**Flamed**

CfA ISO 14001 Quality Management UKAS 0120 · CfA ISO 9001 Environmental Management UKAS 0120 · Ethical Stone Register Declaration Level · Federation Stone Great Britain · NBS Source Manufacturer Partner

*Specification & technical data aligns with our most recent testing, but is indicative and should be treated as such. Images are for illustrative purposes only, exact colours may vary.*